SAFETY DATA SHEETS

This SDS packet was issued with item:

072361624

The safety data sheets (SDS) in this packet apply to the individual products listed below. Please refer to invoice for specific item number(s).

072361608 072361616 072361632 072361640

Eye Protection: Safety goggles

Gloves: Surgical, rubber/PVC gloves Other Clothing and Equipment: Face Mask

Respiratory: None

DANVILLE PROVISIONAL COMPOSITE



TurboTemp 2[™]

SECTION IX - PHYSICAL AND CHEMICAL PROPERTIES

Ventilation: None required, local exhaust recommended

SECTION VIII - EXPOSURE CONTROLS/PERSONAL PROTECTION

Vapor Pressure: Negligible Vapor Density: >1 Evaporation Rate: < I Solubility in Water: Slight Boiling Point: ND Specific Gravity: >1

Appearance and Odor: Tooth colored paste, slight odor

SECTION X - STABILITY AND REACTIVITY

Stable (x) Unstable ()

Conditions to Avoid: Heat in excess of 25°C, direct sunlight or intense light.

Incompatibility: Free radical initiators, oxidizing agents Hazardous Decomposition Products: Acrylic smoke Hazardous Polymerization: May occur () Will not occur (x)

SECTION XI - TOXICOLOGICAL INFORMATION

Carcinogens: None known.

SECT ION XII: ECOLOGICAL INFORMATION

This material contains hazardous components. Allow materials to

cure prior to disposal.

SECTION XII: DISPOSAL CONSIDERATIONS

Dispose of safely in accordance with local, state, and federal regulations.

SECTION XIV: TRANSPORT INFORMATION

Stable under normal conditions of use, transportation, and storage.

SECTION XV: REGULATORY INFORMATION

SECTION XVI: OTHER INFORMATION

None

The data and information given in this msds are accurate on the date of preparation. It does not indicate any warranty or representation. We disclaim all liability relating to use of this material since this is beyond our control.



INSTRUCTIONS

Turbo Temp 2[™] is a unique 4:1, syringeable bis-acryl composite for temporary restorations. Turbo Temp is fast and accurate, especially when used in conjunction with a quality vinyl polysiloxane impression material such as Star VPS (available from Danville Materials).

TURBO TEMP KIT

Turbo Temp comes in a 76 gm automix cartridge. Ten waste-saver tips are included per kit. (Extra tips 10/pk, Order No. 90162, 50/pk, Order No. 90163).

Turbo Temp cartridges are designed to fit on a new style automix gun Order No. 90176.

It is important not to remove the cap on the cartridge until use. After use, leave the used tip on the cartridge. The hardened resin in the tip acts as a cap until the next use.

IMMEDIATELY PRIOR TO USE

Remove cap and eject about a pea size quantity of material out of the bare cartridge end. Eject slowly until steady flow exudes from both compartments. Wipe off the end (without cross mixing) and install the mixing tip.

BEFORE THE PREP

Make initial impression. Place some flexible vinyl polysiloxane (Star VPS Monophase recommended) on a posterior type bite tray and have patient close. Stiff heavy body materials must be avoided, as once removed, they do not go back well into undercuts. Alginate will also serve as a less satisfactory alternative.





An inexpensive bite tray is recommended for the initial impression. The small bite tray requires less impression material.

PREP AND FINAL IMPRESSION

Cut preparation. Take a final impression for the lab. Use a triple tray. Dual viscosity vinyl polysiloxane impression materials are recommended.

AFTER THE PREP

Once the prep and the lab impression have been completed, you are ready to make the temporary. Working time is only 30 to 40 seconds. Set time is 1-1/2 minutes after placement in mouth and full hardness is 3 to 4 minutes. Inject Turbo Temp into the prep areas of the preliminary impression. Use care to avoid trapping air bubbles. Have patient close on tray. Choose cementation technique A or B.

A. Cementation Method (Recommended Technique)

I. Remove the tray I-3/4 to 2 minutes after the mix was injected. The temporary will be retained in the tray and will be slightly flexible. Break off the excess material around the temp while it is still in the impression. This excess should be thin and flexible and can be trimmed easily with an

2. Immediately reset the temp in the mouth and wait I or 2 more minutes for the completion of cure.

- 3. Remove again, wait 4-5 minutes, and pop the temp out of impression.
- 4. Trim margins with a diamond (it is now rigid).
- 5. Cement in place, using a non-eugenol temporary cement.

B. Non-Cementation Method

- 1. Leave Turbo Temp in the mouth during the initial insertion for 2 ½ minutes. It will shrink to fit. It is recommended to cut an escape route in the facial surface of the impression. This will allow excess Turbo Temp to escape, thereby reducing flashing.
- 2. Remove impression from mouth; the temporary should remain in the mouth.
- 3. Trim excess with the scalpel blade or a diamond bur if necessary.

Note: Some non-cemented Turbo Temp restorations may turn dark after two weeks. To avoid this, either place permanent restoration within two weeks or cement the temporary restoration.

Turbotemp 2 bridge fabrication:

Three units is the recommended maximum span. To add strength the proximals of posteriors, the connector areas should be modified to add bulk, prior to taking the preliminary impression. In the posterior, both buccal and lingual can be modified. In the anterior, most of the modification would be done on the lingual to preserve esthetics. The preferred block-out material is Ultradent Blue Bolckout, but soft wax can also be used.

Reinforcement can also be used in addition:

Take the preliminary impression. Then place a piece of Ribbond or some other fibers, from mesial to distal, using cured flowable composite to hold it on preps. The entire piece of reinforcement should be infused with flowable composite. A figure 8 configuration might be considered. No bonding is used so that the reinforcement will be retrievable with the temporary restoration. In the usual manner, form the Turbotemp 2 over the reinforcement. Do not disturb the oxygen inhibited outer layer on the flowable so the Turbotemp 2 will adhere directly to it.

Trouble Shooting

- When starting with a new cartridge, discard the first pea size amount dispensed through the mixing tip to ensure even mixing.
- Do not remove the mixing tip after each use. Wait until ready to use it again, then install new tip. This will prevent catalyst contamination possibly resulting in a plug.
- Mount the mixing tip in proper alignment. Note that the tips are notched to indicate the proper alignment on the cartridge. By forcing the tip, it can be mounted backwards, resulting in non-setting mixes. (The two sides of the mixing tip have different size bores.)
- A slightly gummy air inhibited layer will remain on the hardened surface of the temporary. This layer allows bubble and margin defects to be minimized by directly bonding with a flowable composite such as StarFlow. The layer is easily removed with ethyl alcohol.
- Exposure to temperatures below 74°F will extend the setting time of Turbo Temp. Set times are based on room temperature material. Refrigeration greatly retards set times.
- Normally there is no need for occlusal adjustments if vinyl polysiloxane is used.
- Before placing a new mix tip, extrude a small amount of material to insure both sides are flowing. Waste a pea size amount of material immediately before use to insure a full mix.

MATERIAL SAFETY DATA

SECTION I - PRODUCT IDENTIFICATION

Company Name: Danville Materials

3420 Fostoria Way Suite A-200

San Ramon, CA 94583

Phone (925)973-0710 Fax: (925) 973-0764 Prepared: December 19, 2011

SECTION II - HAZARD(S) IDENTIFICATION

OSHA Permissible Exposure Limits: None Other Exposure Limit Used: None ACGIH Threshold Exposure Limit: None

Chronic, Other: None

SECTION III - COMPOSITION/INFORMATION ON INGREDIENTS

Hazardous component % by weight:

Multifunctional Methacrylates 30-40 Malyonlurea Derivative Trace Silica Filler 45-50 Polyvinyl esters 5-10

SECTION IV - FIRST AID MEASURES

Primary Routes of Exposure: Skin, ingestion

Signs of Exposure: Severe skin or eye irritation, redness or burning sensation.

Ingestion may cause nausea.

Medical Conditions Generally Aggravated by Exposure: Allergies to methacrylates. First Aid Procedures: For Skin - Wash off infected area with soap and water. For Ingestion -Seek medical advice, carry container with label and MSDS. For Eyes - Rinse immediately with plenty of water and consult physician

SECTION V - FIRE-FIGHTING MEASURES

Flash Point: >100°C

Extinguishing Media: Carbon dioxide, foam, dry chemical

Special Fire Fighting Procedures: None

Flammable limits: ND

Unusual Fire and Explosion Hazards: Polymerizes upon heating.

SECTION VI - ACCIDENT RELEASE MEASURES

None

SECTION VII - HANDLING AND STORAGE

Spill Management: Use absorbent to collect the material. Wash contaminated surfaces with soap and water.

ZEST DENTAL SOLUTIONS

SAFETY DATA SHEET

1. Identification

Product identifier TurboTemp™ 2 & 3

Other means of identification

Document number SDS-013-ZD Rev. B

Recommended use Provisional dental composites.

Recommended restrictions None known.

Manufacturer/Importer/Supplier/Distributor information

Supplier

Company name Danville Materials

Address 2875 Loker Avenue East

Carlsbad, CA 92010

Telephone 1-800-827-7940
Contact Customer Service

E-mail danvillecs@zestdent.com

Website www.zestdent.com

Emergency telephone 800-451-8346 / 760-602-8703

number

2. Hazard(s) identification

Physical hazards Not classified.

Health hazardsSensitization, skinCategory 1B

Environmental hazards Hazardous to the aquatic environment, acute Category 3

hazard

Hazardous to the aquatic environment,

Category 3

long-term hazard

OSHA defined hazards Not classified.

Label elements



Signal word Warning

Hazard statement May cause an allergic skin reaction. Harmful to aquatic life with long lasting effects.

Precautionary statement

Prevention Contaminated work clothing must not be allowed out of the workplace. Avoid release to the

environment. Wear protective gloves.

Response If on skin: Wash with plenty of water. If skin irritation or rash occurs: Get medical advice/attention.

Wash contaminated clothing before reuse.

Storage Store away from incompatible materials.

Disposal Dispose of contents/container in accordance with local/regional/national/international regulations.

Hazard(s) not otherwise

classified (HNOC)

None known.

Supplemental information None.

3. Composition/information on ingredients

Mixtures

TurboTemp™ 2 & 3 SDS US

941554 Version #: 07 Revision date: 03-December-2018 Issue date: 21-February-2018

Chemical name	CAS number	%
Ethoxylated bisphenol A dimethacrylate	41637-38-1	20 - 50
Diurethane dimethacrylate	72869-86-4	3 - 20
Fused silica	Proprietary	1 - 15

Composition comments

All concentrations are in percent by weight unless otherwise indicated. Components not listed are either non-hazardous or are below reportable limits.

The manufacturer has claimed one or more hazardous ingredients as trade secret under the OSHA Hazard Communication Standard. The hazards of this (these) ingredient(s) are given on this SDS.

4. First-aid measures

Inhalation Move to fresh air. Call a physician if symptoms develop or persist.

Skin contact Remove contaminated clothing immediately and wash skin with soap and water. In case of eczema or other skin disorders. Seek medical attention and take along these instructions.

Rinse with water. Get medical attention if irritation develops and persists.

Eve contact

Rinse mouth. Get medical attention if symptoms occur. Ingestion May cause an allergic skin reaction. Dermatitis. Rash. Most important

symptoms/effects, acute and delayed

Indication of immediate medical attention and special treatment needed

Provide general supportive measures and treat symptomatically. Keep victim under observation. Symptoms may be delayed.

General information Ensure that medical personnel are aware of the material(s) involved, and take precautions to protect themselves. Wash contaminated clothing before reuse.

5. Fire-fighting measures

Suitable extinguishing media

Unsuitable extinguishing media

Water fog. Foam. Powder. Carbon dioxide (CO2).

Do not use water jet as an extinguisher, as this will spread the fire.

Specific hazards arising from the chemical

Special protective equipment and precautions for firefighters During fire, gases hazardous to health may be formed.

Self-contained breathing apparatus and full protective clothing must be worn in case of fire.

Fire fighting equipment/instructions

Specific methods General fire hazards Move containers from fire area if you can do so without risk. Cool containers exposed to flames

with water until well after the fire is out.

Use standard firefighting procedures and consider the hazards of other involved materials. Contains one or more components that will burn if involved in a fire.

6. Accidental release measures

Personal precautions, protective equipment and emergency procedures

Keep unnecessary personnel away. Keep people away from and upwind of spill/leak. Wear appropriate protective equipment and clothing during clean-up. Avoid breathing mist/vapors. Do not touch damaged containers or spilled material unless wearing appropriate protective clothing. Ensure adequate ventilation. Local authorities should be advised if significant spillages cannot be contained. For personal protection, see section 8 of the SDS.

Methods and materials for containment and cleaning up Prevent product from entering drains.

Large Spills: Stop the flow of material, if this is without risk. Dike the spilled material, where this is possible. Absorb in vermiculite, dry sand or earth and place into containers. Following product recovery, flush area with water.

Small Spills: Wipe up with absorbent material (e.g. cloth, fleece). Clean surface thoroughly to remove residual contamination.

Environmental precautions

Never return spills to original containers for re-use. For waste disposal, see section 13 of the SDS. Avoid release to the environment. Inform appropriate managerial or supervisory personnel of all environmental releases. Prevent further leakage or spillage if safe to do so. Avoid discharge into drains, water courses or onto the ground.

TurboTemp™ 2 & 3 SDS US

7. Handling and storage

Precautions for safe handling Avoid breathing mist or vapor. Avoid contact with eyes, skin, and clothing. Avoid prolonged

exposure. Persons susceptible to allergic reactions should not handle this product. Provide adequate ventilation. Wear appropriate personal protective equipment. Observe good industrial

hygiene practices.

Conditions for safe storage, including any incompatibilities Store in a well-ventilated place. Store in original tightly closed container. Store away from

incompatible materials (see Section 10 of the SDS).

8. Exposure controls/personal protection

Occupational exposure limits

US. OSHA Table Z-1 Limits for Air Contaminants	(29 CFR 1910.1000)

Components	Туре	Value	Form
Fused silica	PEL	0.05 mg/m3	Respirable dust.
US. OSHA Table Z-3 (29 CFF	R 1910.1000)		
Components	Туре	Value	Form
Fused silica	TWA	0.05 mg/m3	Respirable.
		1.2 mppcf	Respirable.
US. ACGIH Threshold Limit	Values		
Components	Type	Value	Form
Fused silica	TWA	0.025 mg/m3	Respirable fraction.
US. NIOSH: Pocket Guide to	Chemical Hazards		
Components	Type	Value	Form
Fused silica	TWA	0.05 mg/m3	Respirable dust.

Biological limit values

Appropriate engineering controls

No biological exposure limits noted for the ingredient(s).

Good general ventilation should be used. Ventilation rates should be matched to conditions. If applicable, use process enclosures, local exhaust ventilation, or other engineering controls to maintain airborne levels below recommended exposure limits. If exposure limits have not been established, maintain airborne levels to an acceptable level. Eye wash fountain and emergency

Individual protection measures, such as personal protective equipment

showers are recommended.

Wear approved chemical safety goggles. Face shield is recommended. Eye/face protection

Skin protection

Wear appropriate chemical resistant gloves. Suitable gloves can be recommended by the glove **Hand protection**

supplier.

Skin protection

Wear appropriate chemical resistant clothing. Use of an impervious apron is recommended. Other

Respiratory protection None required where adequate ventilation conditions exist. Use a positive-pressure air-supplied respirator if there is any potential for an uncontrolled release, exposure levels are not known, or

any other circumstances where air-purifying respirators may not provide adequate protection.

Wear appropriate thermal protective clothing, when necessary. Thermal hazards

General hygiene considerations

Always observe good personal hygiene measures, such as washing after handling the material and before eating, drinking, and/or smoking. Routinely wash work clothing and protective

equipment to remove contaminants. Contaminated work clothing should not be allowed out of the

workplace.

9. Physical and chemical properties

Appearance

Paste **Physical state Form** Paste.

Color Not available. Not available. Odor **Odor threshold** Not available. pН Not applicable.

TurboTemp™ 2 & 3 SDS US Melting point/freezing point Not available.

Initial boiling point and boiling Not available.

range

Flash pointDoes not flash.Evaporation rateNot available.Flammability (solid, gas)Not applicable.

Upper/lower flammability or explosive limits

Explosive limit - lower (%) Not available.

Explosive limit - upper (%) Not available.

or pressure Not available.

Vapor pressureNot available.Vapor densityNot available.Relative densityNot available.

Solubility(ies)

Solubility (water) Not available.

Partition coefficient Not available.

(n-octanol/water)

Auto-ignition temperatureNot available.Decomposition temperatureNot available.Viscosity> 20.5 mm²/sViscosity temperature104 °F (40 °C)

Other information

Explosive properties Not explosive. **Oxidizing properties** Not oxidizing.

10. Stability and reactivity

ReactivityThe product is stable and non-reactive under normal conditions of use, storage and transport.

Chemical stability Material is stable under normal conditions.

Possibility of hazardous

reactions

No dangerous reaction known under conditions of normal use.

Conditions to avoid Contact with incompatible materials. Excessive heat.

Incompatible materials Strong oxidizing agents. Free radical initiators. Iron.

Hazardous decomposition

products

Thermal decomposition of this product can generate carbon monoxide and carbon dioxide. Silicon

oxide fumes.

11. Toxicological information

Information on likely routes of exposure

InhalationProlonged inhalation may be harmful.Skin contactMay cause an allergic skin reaction.

Eye contact Direct contact with eyes may cause temporary irritation.

Ingestion May cause discomfort if swallowed.

Symptoms related to the physical, chemical and toxicological characteristics

May cause an allergic skin reaction. Dermatitis. Rash.

Information on toxicological effects

Acute toxicity Not expected to be acutely toxic.

Skin corrosion/irritation Prolonged skin contact may cause temporary irritation. **Serious eye damage/eye** Direct contact with eyes may cause temporary irritation.

irritation

Respiratory or skin sensitization

Respiratory sensitization Not a respiratory sensitizer.

Skin sensitization May cause an allergic skin reaction.

Germ cell mutagenicityNo data available to indicate product or any components present at greater than 0.1% are

mutagenic or genotoxic.

TurboTemp™ 2 & 3 SDS US

Carcinogenicity Due to the form of the product, exposure to the potentially carcinogenic components is not

expected.

IARC Monographs. Overall Evaluation of Carcinogenicity

Fused silica (CAS Proprietary) 1 Carcinogenic to humans.

NTP Report on Carcinogens

Fused silica (CAS Proprietary) Known To Be Human Carcinogen.

Reasonably Anticipated to be a Human Carcinogen.

OSHA Specifically Regulated Substances (29 CFR 1910.1001-1053)

Fused silica (CAS Proprietary) Cancer

Reproductive toxicityThis product is not expected to cause reproductive or developmental effects.

Specific target organ toxicity -

single exposure

Not classified.

Specific target organ toxicity -

repeated exposure

Not classified.

Aspiration hazard Not an aspiration hazard.

Chronic effects Prolonged inhalation may be harmful.

12. Ecological information

Ecotoxicity Harmful to aquatic life with long lasting effects.

Persistence and degradability No data is available on the degradability of this product.

Bioaccumulative potential

Partition coefficient n-octanol / water (log Kow)

Ethoxylated bisphenol A dimethacrylate (CAS 41637-38-1) 5.3 - 5.62

Mobility in soil No data available for this product.

Other adverse effects None known.

13. Disposal considerations

Disposal instructions Collect and reclaim or dispose in sealed containers at licensed waste disposal site. Dispose of

contents/container in accordance with local/regional/national/international regulations.

Local disposal regulations Dispose in accordance with all applicable regulations.

Hazardous waste code

The waste code should be assigned in discussion between the user, the producer and the waste

disposal company.

Waste from residues / unused

products

Dispose of in accordance with local regulations. Empty containers or liners may retain some product residues. This material and its container must be disposed of in a safe manner (see:

Disposal instructions).

Contaminated packaging Since emptied containers may retain product residue, follow label warnings even after container is

emptied. Empty containers should be taken to an approved waste handling site for recycling or

disposal.

14. Transport information

DOT

Not regulated as dangerous goods.

IATA

Not regulated as dangerous goods.

IMDG

Not regulated as dangerous goods.

Transport in bulk according to Not established.

Annex II of MARPOL 73/78 and

the IBC Code

15. Regulatory information

US federal regulationsThis mixture is a product regulated by the FDA. Within the meaning of the OSHA Hazard

Communication Standard [29 CFR 1910.1200]: this mixture is considered hazardous.

TSCA Section 12(b) Export Notification (40 CFR 707, Subpt. D)

Not regulated.

CERCLA Hazardous Substance List (40 CFR 302.4)

Not listed.

TurboTemp™ 2 & 3 SDS US

SARA 304 Emergency release notification

Not regulated.

OSHA Specifically Regulated Substances (29 CFR 1910.1001-1053)

Fused silica (CAS Proprietary)

Cancer
lung effects

immune system effects

kidney effects

Superfund Amendments and Reauthorization Act of 1986 (SARA)

SARA 302 Extremely hazardous substance

Not listed.

SARA 311/312 Hazardous

Yes

chemical

Classified hazard

Respiratory or skin sensitization

categories

SARA 313 (TRI reporting)

Not regulated.

Other federal regulations

Clean Air Act (CAA) Section 112 Hazardous Air Pollutants (HAPs) List

Not regulated.

Clean Air Act (CAA) Section 112(r) Accidental Release Prevention (40 CFR 68.130)

Not regulated.

Safe Drinking Water Act

Not regulated.

(SDWA)

US state regulations

US. Massachusetts RTK - Substance List

Fused silica (CAS Proprietary)

US. New Jersey Worker and Community Right-to-Know Act

Fused silica (CAS Proprietary)

US. Pennsylvania Worker and Community Right-to-Know Law

Fused silica (CAS Proprietary)

US. Rhode Island RTK

Fused silica (CAS Proprietary)

California Proposition 65

California Safe Drinking Water and Toxic Enforcement Act of 2016 (Proposition 65): This material is not known to contain any chemicals currently listed as carcinogens or reproductive toxins. For more information go to www.P65Warnings.ca.gov.

US. California. Candidate Chemicals List. Safer Consumer Products Regulations (Cal. Code Regs, tit. 22, 69502.3, subd. (a))

Fused silica (CAS Proprietary)

16. Other information, including date of preparation or last revision

Issue date21-February-2018Revision date03-December-2018

Version # 07

NFPA ratings



Disclaimer

Danville Materials cannot anticipate all conditions under which this information and its product, or the products of other manufacturers in combination with its product, may be used. It is the user's responsibility to ensure safe conditions for handling, storage and disposal of the product, and to assume liability for loss, injury, damage or expense due to improper use. The information in the sheet was written based on the best knowledge and experience currently available.

TurboTemp™ 2 & 3 SDS US